

06/01/00

PTO
09/584701
06/01/00

06/01/00

Please type a plus sign (+) inside this box → ☐Approved for use through 09/30/2000 CMB 0561-0032
Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PTO/SB/05 (2/99)

UTILITY PATENT APPLICATION TRANSMITTAL (Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))	Attorney Docket No.	SLA 001
	First Inventor or Application Identifier	Irene Lin
	Title	Method for manufacturing an air permeable composite film
	Express Mail Label No.	

APPLICATION ELEMENTS See MPEP chapter 600 concerning utility patent application contents		ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20541	
1. <input checked="" type="checkbox"/> * Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing)	6. <input type="checkbox"/> Microfiche Computer Program (Appendix)		
2. <input checked="" type="checkbox"/> Specification [Total Pages 27] (preferred arrangement set forth below) - Descriptive title of the invention - Cross References to Related Applications - Statement Regarding Fed sponsored R & D - Reference to Microfiche Appendix - Background of the invention - Brief Summary of the invention - Brief Description of the Drawings (if filed) - Detailed Description - Claim(s) - Abstract of the Disclosure	7. Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary) a. <input type="checkbox"/> Computer Readable Copy b. <input type="checkbox"/> Paper Copy (identical to computer copy) c. <input type="checkbox"/> Statement verifying identity of above copies		
3. <input checked="" type="checkbox"/> Drawing(s) (35 U.S.C. 113) [Total Sheets 4]	ACCOMPANYING APPLICATION PARTS 8. <input type="checkbox"/> Assignment Papers (cover sheet & document(s)) 9. <input type="checkbox"/> 37 C.F.R. §3.73(b) Statement (when there is an assignee) <input checked="" type="checkbox"/> Power of Attorney 10. <input type="checkbox"/> English Translation Document (if applicable) 11. <input type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input type="checkbox"/> Copies of IDS Citations 12. <input type="checkbox"/> Preliminary Amendment 13. <input type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized) 14. <input checked="" type="checkbox"/> * Small Entity Statement(s) <input type="checkbox"/> Statement filed in prior application, Status still proper and desired (PTO/SB/09-12) 15. <input type="checkbox"/> Certified Copy of Priority Document(s) (if foreign priority is claimed) 16. <input type="checkbox"/> Other:		
4. Oath or Declaration [Total Pages 2] a. <input checked="" type="checkbox"/> Newly executed (original or copy) b. <input type="checkbox"/> Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 17 completed) [Note Box 5 below] i. <input type="checkbox"/> <u>DELETION OF INVENTOR(S)</u> Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).	* NOTE FOR ITEMS 1 & 14: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).		
5. <input type="checkbox"/> Incorporation By Reference (Use only if Box 4b is checked) The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b, is considered to be part of the disclosure of the accompanying application and is hereby incorporated by reference therein.			
17. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information below and in a preliminary amendment. <input type="checkbox"/> Continuation <input type="checkbox"/> Divisional <input type="checkbox"/> Continuation-in-part (CIP) of prior application No. _____ Prior application information: Examiner _____ Group/Art Unit: _____			
18. CORRESPONDENCE ADDRESS <input type="checkbox"/> Customer Number or Bar Code Label (Insert Customer No. or Attach bar code label here) or <input checked="" type="checkbox"/> Correspondence address below			
Name	Winston Hsu		
Address	3F, No. 52, Lane 46, Ming-sheng Rd., 234 Yunghe City, Taipei Hsien, Taiwan, R.O.C.		
City	State	Zip Code	234
Country	Telephone	Fax	Taiwan, R.O.C. 886-2-2948-3200 886-2-2948-6200

Name (Print/Type)	Winston Hsu	Registration No. (Attorney/Agent)	41,526
Signature	Winston Hsu	Date	05/30/2000

Read the Statement. This form is estimated to take 12 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20541. (DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20541)

SLA 001

Filed or Issued:

☐ the patent identified above.

☐ Each such person, concern, or organization is listed below.

Date _____

METHOD FOR MANUFACTURING AN AIR PERMEABLE COMPOSITE FILM

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to a method for manufacturing an air permeable composite film. More particularly, the method relates to a method for manufacturing a composite film with superior air and moisture vapor permeability, which is particularly suited for microwave heating.

2. Description of the Prior Art

A wide variety of air and moisture vapor permeable materials have been developed for different purposes. For example, these materials can be used in filtration and separation. In U.S. Pat.No.5,928,582, for example, there is disclosed a method of forming a microporous membrane that uses a process of ultraviolet irradiation to form microsphereulites, followed by a thermally-induced phase separation, yielding microporous membranes that have improved flow and mechanical properties. In U.S. Pat.No.5,865,926, Wu et al. disclose a method of making a cloth-like microporous laminate of a non-woven fibrous web and thermoplastic film having air and moisture vapor permeability with liquid-barrier properties.

Other manufacturing processes for production of relevant microporous films are known in U.S. Pat. Nos .3,378,507; 3,310,505; 3,607,793; 3,812,224; 4,247,498 and 4,466,931. For example, in U.S. Pat. No. 4,350,655, Hoge teaches a process for manufacturing a highly porous thermoplastic film formed by cold drawing a film of a synthetic thermoplastic orientative polymer, such as high-density polyethylene, admixed with a coated inorganic filler.

The highly porous thermoplastic film is produced by first casting a film of a blend of the polymer-coated inorganic filler mixture, cooling the film to a temperature of 70°C and cold stretching the film mono-axially or bi-axially to develop the desired void volume and surface ruptures per unit area, thereby obtaining a resin content (by weight) per cubic centimeter of final product of about 0.18 to about 0.32 gm/cc.

The coated inert inorganic filler and the molten polymer are blended together to form a homogeneous mixture in a suitable mixing extruder. The molten mixture is extruded through a die with an opening from 0.006 inches to 0.010 inches in size. The blend is cold stretched mono-axially or bi-axially, preferably in a station provided with a set of grooved rollers. The groove pattern of the rolls is generally of a sinusoidal wave pattern, wherein the film is stretched in a manner to affect uniform stretching between contact points of the material to produce a material of larger dimension in the stretching direction.

Disadvantageously, however, the manufacturing processes of microporous film products according to the prior art methods are too complicated and too expensive to be generally accepted. Furthermore, many operating factors, such as temperature, stretching ratios, film thickness, starting materials etc., affect the microporous size of the final products, and thus result in variations of the quality of the microporous film products. In addition, the filler added to the microporous film products according to the prior art methods is a source of environmental pollution. Furthermore, most of the film products according to the prior art methods are opaque due to the multiple phases of the film products that result from the addition of fillers.

When food has, heretofore, been cooked at home, the food has been wrapped in a wrapping film for home use, or was packed and sealed in an air or moisture impermeable bag. This is heated in a microwave oven. Moisture contained in the food evaporates, and the bag is thus burst by internal pressure. Moreover, when the film products according to the prior art methods are used to form a food-packaging bag, some of the fillers may contaminate the food within the bag, which results in unpleasant odors. Another disadvantage of the film products according to the prior art methods is that they have poor resistance to alcohol and oil.

SUMMARY OF THE INVENTION

It is therefore a primary objective of this invention to provide a novel air permeable composite film and manufacturing method thereof to improve the prior art method.

Another objective of the present invention is to provide a novel air permeable composite film with superior oil and alcohol resistance, and strength against stress.

Still another objective of the present invention is to provide a method for making a food packaging bag for microwave heating formed by virtue of the novel air permeable composite films.

In accordance with the present invention, there is provided an air permeable composite film comprising a polymer layer having a top face and a bottom face and a sealing layer that covers the top face of the air permeable composite film. The polymer layer is subjected to an impression process and is perforated to form a plurality of gaps thereon. After performing a thermal process, the molten sealing layer fills the gaps.

09584701.060100
In accordance with the processing aspect of the present invention, the air permeable composite film is produced by first providing a polymer layer having a top face and a bottom face, then performing an impression process to perforate the polymer layer so as to form a plurality of gaps on the top face of the polymer layer. Before performing the impression process, a first coating process is performed to form a sealing layer that is used to fill the gaps on the top face of the polymer layer. In another embodiment, the sealing layer is coated after the impression process. The sealing layer keeps the gaps sealed and air impermeable and provides the air permeable composite film with water repelling abilities when the differential pressure between the top face and the bottom face of the air permeable composite film is zero or approximately zero. When the differential pressure grows, the gap, acting as a ventilating perforation, becomes air and vapor permeable.

The sealing layer is made of a material selected from a group consisting of lipids, oleaginous materials, wetting agents, surfactants, waxes, fatty acids and their derivatives, starch, or amyloid materials and their derivatives. The waxes include natural waxes and synthetic waxes. The natural waxes include palm waxes, paraffin waxes, micro-crystalline waxes, beeswax and rice bran waxes. The synthetic waxes include synthetic polyethylene (PE) waxes, synthetic polypropylene (PP) waxes, synthetic polyethylene oxide (PEO) waxes and polyolefin.

In accordance with the present invention, there is provided an air permeable packaging bag comprising a folded polymer layer with three overlapping sealed edges and one open end. The folded polymer layer has a plurality of gaps formed by virtue of an

impression process. In order to seal the gaps so as to provide the air permeable packaging bag with water repelling abilities and air impermeability when the internal pressure inside the air permeable packaging bag is small compared to the outside pressure, a sealing layer is formed on the surface of the folded polymer layer. When the internal pressure inside the air permeable packaging bag grows, the gaps, like ventilating perforations, become air and vapor permeable. The open end can be sealed using a zipper, an adhesive tape, an ultrasonic pressing process, or a thermal pressing process so as to form a sealed packaging bag.

As the temperature rises, when the package bag is subjected to a microwave oven, due to the vibration and abrasion of the molecules within the packaged food, the energy of microwave is converted to heat and the temperature and the vapor pressure inside the packaging bag also rises. When the differential pressure between the atmosphere and the inside of the packaging bag increases, the internal vapor pressure causes the packaging bag to inflate, which enlarges the gaps. In addition, the heat causes the sealing material to thin, making it permeable. Under these conditions the gaps become air and vapor permeable. The gaps in the present invention act as a pressure-releasing valve that prevents bursting of the packaging bag.

In accordance with the processing aspect of the present invention, the air permeable packaging bag is manufactured by first providing two polymer layers on which at least one of the two polymer layers comprises a plurality of gaps formed by virtue of an impression process. The two polymer layers are overlapped, and a sealing process seals three of the overlapping edges of the two polymer layers, leaving an opening in the air permeable packaging bag. A sealing layer is formed on the surface of the

09584701.0601.00

Please refer to Fig.1A to Fig.1C. Fig.1A to Fig.1C are cross-sectional diagrams of the structures of air permeable composite films before performing an impression process according to the present invention. As shown in Fig.1A, a structure 100, in this embodiment a polymer composite layer is provided. The structure 100 is made of a material selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or polyurethane (PU).

As shown in Fig.1B, the structure 100 can be a stacked laminate including a first layer 10 and a second layer 20. The first layer 10 is made of a material selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or polyurethane (PU). The second layer 20 is made of a material selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether

ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or polyurethane (PU), synthetic papers, glassine papers, polyolefin coated paper or paper-like materials. For commercial purposes,
5 the first layer 10 and the second layer 20 are preferably made of transparent materials.

As shown in Fig.1C, the structure 100 can also be a sandwiched structure comprising a first layer 10, a second layer 20 stacked
10 on the first layer 10, and a third layer 30 stacked on the second layer 20. The first layer 10 is made of a material with a relatively low melting point selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin,
15 polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or
20 polyurethane (PU). The second layer 20 and the third layer 30 are made of materials selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA),
25 SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or polyurethane (PU), synthetic papers, glassine papers, or paper-like materials.

Please refer to Fig.2A to Fig.2C. Fig.2A to Fig.2C are cross-sectional diagrams of air permeable structures 102 after

performing an impression process according to the present invention. These figures are in respective combination with Figs.1A to Fig.1C. The structures 100 in Fig.1A to Fig.1C are partially or totally perforated by virtue of an impression process
5 in a direction from the top face 12 to the bottom face 14, which forms a plurality of tiny gaps 15 on the structures 102 in Fig.2A to Fig.2C. After the impression process, the structures 100 in Figs.1A to 1C are permanently damaged, forming the structures 102 in Figs.2A to 2C, respectively. When the structure 102 is in a
10 static state, and without any external stress applied to it, the gaps 15 are approximately closed (pseudo-closed) and the surface of the structure 102 has a pseudo-planar topography with multiple phases. When the structure 102 swells due to external pressure, the gaps 15 enlarge.

15

The impressed area can be selected as desired to form a random impressed pattern, or the whole area can be impressed. Both continuous-type impression cylinder roller sets and batch-type planar table-like impression machines are suitable for the
20 impression process. The former, however, is more economical, and is more easily automated. The continuous-type impression cylinder assembly comprises an impression cylinder and one opposing cylinder. Both the cylinder roller set and planar table-like machine include an impresser and a transfer co-impresser. At least
25 one of the two impressers comprises a plurality of fine protruding grains on the surface of the cylinder or plate (not shown). The protruding grains may be formed using the following methods: (1) electroplating polyhedron diamond-like powders onto the surface of the impresser; (2) using a laser to engrave ceramic materials
30 or metals formed on the surface of the impresser, such as anilox rolls; (3) using a mechanical tooling method and performing a surface hardening treatment, such as an annealing process, on the

metal formed on the surface of the impresser, or plating a hard coating material on the surface of the impresser following a thermal treatment; (4) electrochemically etching and then performing a surface hardening treatment on the surface metal of the impresser. In addition, the opposing cylinder or plate, i.e. the co-impresser, should be made of a metal with a relatively high hardness, such as steel, or ceramic.

Please refer to Fig.3. Fig.3 depicts a top view of the gaps 15, with a cruciform shape, on the surface of the air permeable composite film structure 102 according to the present invention. It should be noted that the gaps 15 may have other shapes. Preferably, the shape of the gaps 15 are selected from groups consisting of linear shapes, conic shapes, pyramidal shapes, tetrahedral shapes, polygonal shapes, or cruciform shapes. Basically, the shape of the gaps 15 depends on the shape of the protruding grains on the surface of the cylinder or plate. The gaps 15 can be evenly distributed, locally distributed, regularly distributed, or irregularly distributed within the selected areas on the surface of the air permeable composite film structure 102, depending on the condition of the cylinders, sealing materials and the function of the air permeable composite film structure 102.

Please refer to Fig.4. Fig.4 is a cross-sectional diagram of the structure 102 in Fig.2A with a sealing layer 16 on the top face 12 of the polymer layer 10 according to the present invention. A sealing layer 16 can be optionally coated onto the top face 12 of the polymer layer 10. Similarly, the sealing layer 16 can also be coated onto the polymer layer 10 of Fig.2B and Fig.2C. The sealing layer 16 provides the structure 102 with waterproofing abilities, and better thermal insulating properties. The sealing

layer 16 keeps the gaps 15 both sealed and air impermeable, and provides the structure 102 with water repelling abilities when the differential pressure between the top face 12 and bottom face 14 is approximately zero. When the differential pressure between the top face 12 and bottom face 14 becomes larger, the gaps 15 become air and vapor permeable. The sealing layer 16 may be coated by a sealing material prepared in an emulsion solution type, dispersion solution type, or a micronized powder type.

Preferably, the sealing layer 16 is made of a material selected from a group comprising lipids, oleaginous materials, wetting agents, surfactants, fatty acids and their derivatives, starch, or amyloid materials and their derivatives, palm waxes, paraffin waxes, micro-crystalline waxes, beeswax, rice bran waxes, synthetic polyethylene (PE) waxes, synthetic polypropylene (PP) waxes, synthetic polyethylene oxide (PEO) waxes and polyolefin. When the composite film structure 102 comes into contact with hot air, the heat of the hot air will degrade the sealing ability of the sealing layer 16, opening the pseudo-closed tiny gaps 15, and the hot air can easily permeate through the sealed gaps 15 of the polymer composite layer when the air pressure exerted by the hot air on the first side of the composite film is greater than the air pressure on the other side of the composite film structure 102. On the other hand, when the heating source is removed, the temperature of the composite film structure 102 decreases and the sealing layer 16 regains its sealing abilities. The sealing layer 16 used to fill the gaps 15 can be formed either before or after the impression process.

The method of the present invention further comprises a thermal process that is used to melt the sealing layer 16 so as to improve the sealing of the gaps 15. If the structure 102 is used for food

packaging, the sealing layer 16 is preferably an esculent wax certified by the FDA, which is imperceptible during the use of the structure 102, and should not influence the luster, printablility, or sealing of the structure 102. The preferable
5 melting point of the sealing layer 16 is between 40 to 110 °C. In the preferred embodiment, Paraffin is used due to its superior water repelling characteristics, and because of its vapor permeability. Moreover, some oxygen scavengers, or oxidizable metal components, such as iron, aluminum, zinc, nickel, copper,
10 manganese, sodiumbisulfate, sulfamic acid, ferrous sulfate, zinc sulfate, etc., can be blended into the sealing layer 16 and/or polymer layer 10 to prevent oxidation and putrefaction of food packed using the structure 102.

15 Please refer to Fig.5. Fig.5 is a schematic diagram of an air permeable packaging bag 110 made of the structure 102 in Fig.2A to Fig.2C according to the present invention. It should be noted that the structure 102 of the air permeable packaging bag 110 of the present invention can be made from any of the structures 102
20 shown in Fig.2A to Fig.2C. An air permeable structure 102, either from Fig.2A, Fig.2B, or Fig.2C, is first provided. A sealing material, as earlier mentioned, is coated on the surface of the structure 102 to improve the thermal insulation properties of the air permeable packaging bag 110. But, as noted, such a coating
25 is not essential for this invention. The structure 102 is folded along the middle line 25 to superimpose the folded structure 102 upon itself, the sealing material being coated on the inner surface of the folded structure 102. The two overlapping edges 22 are then sealed so as to form an open end 17. In forming the packaging bag
30 110 of this invention, by virtue of the usage and application of transparent polymer materials, the printing upon the surface of the packaging bag 110 can be designed to allow a see-through

picture of the food that is contained within the packaging bag 110. Thus, consumers can be assured that the product purchased is exactly what they want, and has been processed in a suitable manner.

5

Please refer to Fig.6. Fig.6 is a schematic diagram of another embodiment of an air permeable packaging bag 120 made of the air permeable composite film according to the present invention. As shown in Fig.6, the air permeable packaging bag 120 is formed by superimposing a film 104 and a film 106, sealing three of the overlapping edges 32 to leave an open end 50. The three overlapping edges 32 can be sealed using a zipper, an adhesive tape, an ultrasonic pressing process, or a thermal pressing process.

15 After the food is packed into the packaging bag 120, the open end 50 is sealed using a zipper, sliding zipper, an adhesive, an ultrasonic pressing process, or a thermal pressing process to form a sealed packaging bag 120. As seen in Fig.6, in this embodiment, a zipper 40 consisting of a groove and a rib on each film 104 and 20 106 is used to form an interlocking mechanism that can be conveniently opened and re-sealed by consumers. The zipper 40 is easily grasped. When the zipper 40 is pulled, the open end 50 of the packaging bag 120 can be completely opened, and the contents easily removed from the packaging bag 120. It should be noted that 25 the type of adhesive used in the fabrication of this invention should be one that is heat resistant. The manufacturer may wish to use a thermally setting adhesive. Such an adhesive, when initially applied to the packaging bag 120, will maintain adhesion, and will not weaken, fracture, or soften, particularly when 30 exposed to the heat generated by a microwave cooking cycle.

The air permeable packaging bag 120 of the present invention

can be used in the packaging of a variety of foodstuffs, such as frozen food products, popcorn, or other substances. The foods packed within the air permeable packaging bag, and which are to be cooked, can be directly heated by means of a microwave oven, steam, boiled water or infrared irradiation. At the beginning of the microwave heating process, the packed food is under a low-temperature condition, and the vapor pressure inside the sealed packaging bag is low. The gaps on the surface of the packaging bag are thus sealed and air impermeable. At this phase, most of the microwave energy is kept in the packaging bag and transferred to a state of heat that provides a uniform heating effect on the food. As the temperature rises, the vapor pressure inside the sealed packaging bag also rises. When the differential pressure between the atmosphere and the inside of the packaging bag increases, the internal vapor pressure inflates the packaging and thus enlarges the gaps. When the temperature reaches the softening point of the sealing material, the sealing layer becomes malleable because of the heat, and the thickness of the sealing layer begins to lessen and/or the gaps may start opening up. That makes the gaps become air and vapor permeable. The gaps in the present invention act as a pressure-releasing valve that prevents the breakage or bursting of the packaging bag due to the buildup of hot air and steam during a microwave heating process.

It is advantageous to use the air permeable packaging bag of the present invention because the final condition of the food can be finely controlled by using different recipes in combination with the number of gaps, shape of the gaps, density of the gaps, distribution of the gaps, film thickness of the packaging bag, starting material of the packaging bag, and the material used in the sealing layer. In addition, cooked food packed in the sealed packaging bag can be frozen or heated repeatedly without impairing

the taste of the food, as the structure of the air permeable packaging bag can be restored to its original condition.

One of the main features of the invention is that the packaging bag 120 can be used for comestible articles that are to be cooked in a microwave oven with a uniform cooking result. It also prevents the excessive loss of food constituents, such as water, alcohol, fat, flavor, aromatics and other special components. It provides a means for reducing the criticality of the microwave cooking time, as well as reducing the attention and activity associated with conventional microwave cooking. More particularly, the present invention enables the cooking of frozen foods in microwave ovens without having to initially thaw the food, and/or without having to provide power level changes to sequentially effect thawing and cooking. The packaging bag 120 of this invention can be refrigerated or frozen during the storage of the contained product, and functions very effectively under such conditions. Also, the packaging bag 120 of this invention provides a low-cost, self-identifying microwave-cooking container that may also be used for leftovers and home-frozen foods.

In order to ensure a germ, bacteria and fungus free environment when packaging food and medical clinical articles, food or clinical swabs can be sealed in the packaging bag 120 followed by a high-temperature sterilization, sanitizing and/or ultraviolet radiation treatment. During the sterilization process, the bag inflates and the sealing ability of the sealing material decreases. Hot and high pressure air ventilates through the gaps in the permeable packaging bag. After the sterilization process, the temperature of the packaging bag returns to room temperature. The molten sealing material solidifies and re-seals the gaps while the temperature decreases. The sealing abilities

of the sealing material returns. Additionally, the packaging bag will have the appearance of a vacuum-packed bag due to volume contraction at a lower temperature. Therefore, the storage period of germ-free packaged food or clinical products is extended.

5 Therefore, this process is most convenient for cooking fresh meat within the sealed bag and the sealed cooked meat can be frozen and be re-heated with microwave oven directly. Most importantly, the packaging bag 120 can be made almost fully transparent. And as previously explained, the packaging bag 120 is re-usable, and
10 may be used repeatedly for leftovers, for freezing or refrigeration, or for general storage, and subsequent re-heating within a microwave oven.

In addition, the air permeable structure of the invention can
15 be manufactured to form a variety of bags, such as back-sealed bags, gadget bags, three-sided bags or standing pouches. Notably, soups and stews can be packaged using a standing pouch, which is designed to have a pseudo air permeable structure at the top portion of the standing pouch above the level of the soup or stew.
20 When the pouch is cooked in a microwave oven and the soup begins to boil, the hot, high-pressure air ventilates through the opened gaps at the top of the standing bag, and so the bag does not burst.

In another embodiment according to this invention, the air
25 permeable structure 102 can also be used in combination with a microwave tray (not shown) for cooking food. The microwave tray, made of heat resistant materials such as polymeric materials, ceramics, glasses, polyolefin coated paper, wood or bamboo materials, can have spaces with different sizes, and is used to
30 hold the food for cooking. The tray has an open rim on its outer peripheral area. The air permeable structure 102 of the invention is used to seal the microwave tray, covering the food held by the

microwave tray. The open rim of the microwave tray is snugly sealed using methods mentioned earlier, such as a thermal pressing method, or by using a rim secure socket, a ziplock, sliding zipper, a heat sealing process, an ultrasonic pressing process or an adhesive.

5 Browning, crisping, or singeing, can be achieved by coating and/or blending a unique heat or temperature enhancing material, such as carbon black or metallic powder, within selected areas of the microwave tray. Such materials are capable of converting more microwave energy to heat within those selected areas, creating
10 higher temperatures.

Those skilled in the art will readily observe that numerous modifications and alterations of the device may be made while retaining the teachings of the invention. Accordingly, the above
15 disclosure should be construed as limited only by the metes and bounds of the appended claims.

CLAIMS

What is claimed is:

1. A composite film comprising:
 - 5 a polymer composite layer having two sides with a plurality of pseudo-closed tiny gaps for air permeation; and a nonstick sealing layer attached to one side of the polymer composite layer for filling the gaps to prevent air permeation;
 - 10 wherein when heated by hot air, the heat of the hot air will degrade the sealing ability of the sealing layer, or open the pseudo-closed tiny gaps, and the hot air can easily permeate through the sealed gaps of the polymer composite layer when the air pressure exerted by the hot air on the first side of
 - 15 the composite film is greater than the air pressure on the other side of the composite film; on the other hand, when the heating source is removed, the temperature of the composite film decreases and the sealing ability of the sealing layer is restored.
 - 20
2. The composite film of claim 1 wherein the gaps are formed using an impression process.
3. The composite film of claim 2 wherein the impression process
 - 25 is performed after the sealing layer is formed on one side of the polymer layer.
4. The composite film of claim 1 wherein the polymer layer contains one or more layers each made by one of the following
 - 30 materials: acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate

09564701.060100
5 (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA),
Surlyn™ (Dupont ionomer), polyethylene naphthalate (PEN),
poly ether ether ketone (PEEK), polycarbonate (PC),
polysulfone, polyimide (PI), polyacrylonitrile (PAN),
styrene acrylonitrile (SAN), polyurethane (PU), synthetic
papers, glassine papers, polyolefin coated paper or
paper-like materials.

10 5. The composite film of claim 1 wherein the sealing layer is
made from fatty acids or their derivatives, starch, amyloid
materials or their derivatives, lipids, oleaginous materials,
wetting agents, or waxes.

15 6. The composite film of claim 5 wherein the waxes are natural
waxes or synthetic waxes.

20 7. The composite film of claim 1 wherein the gaps are evenly
distributed or distributed within selected areas of the
polymer layer.

8. The composite film of claim 1 wherein the polymer layer or
the sealing layer further comprises an oxygen scavenger for
preventing oxygen from permeating through the composite film.

25 9. The composite film of claim 1 further comprising another
nonstick sealing layer attached to the other side of the
polymer layer for filling the gaps to prevent air permeation.

30 10. A composite film comprising a first layer, and a second layer
laminated on the first layer, the composite film comprising
a top face on the first layer and a bottom face on the second
layer, the composite film being perforated by virtue of an

impression process, thereby forming a plurality of tiny gaps in the composite film for air permeation.

11. The composite film of claim 10 wherein the surface of the composite film comprises a sealing layer that fills the tiny gaps.

12. The composite film of claim 10 wherein the first layer is made from one of the following materials: acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), polyether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), or polyurethane (PU).

13. The composite film of claim 10 wherein the second layer material is composed of a material with a higher melting point than that of the first layer.

14. The composite film of claim 13 wherein the second layer is composed of a material selected from a group comprising acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), SurlynTM (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN), styrene acrylonitrile (SAN), polyurethane (PU), synthetic papers, glassine papers,

polyolefin coated paper or paper-like materials.

15. The composite film of claim 10 further comprising an oxygen scavenger for preventing oxygen from permeating through the composite film.

16. The composite film of claim 10 wherein the sealing layer is made from fatty acids or their derivatives, starch, amyloid materials or their derivatives, lipids, oleaginous materials, wetting agents, or waxes.

17. The composite film of claim 16 wherein the waxes are natural waxes or synthetic waxes.

18. The composite film of claim 10 wherein the gaps are evenly distributed or distributed within selected areas of the polymer layer.

19. A manufacturing method of a composite film comprising:
providing a polymer composite layer having two sides;
performing an impression process to form a plurality of tiny gaps in the polymer composite layer; and
performing a coating process to form a nonstick sealing layer on one side of the polymer composite layer;
wherein the sealing layer is used for filling the gaps of the polymer composite layer to prevent air permeation, and when the composite film is heated by hot air the heat of the hot air will degrade the sealing ability of the sealing layer, or open the gaps, and the hot air can easily permeate through the gaps of the polymer composite layer when the air pressure exerted by the hot air on the first side of the composite film is greater than the air pressure on the other side of the

composite film; on the other hand, when the heating source is removed, the temperature of the composite film will decrease and the sealing ability of the sealing layer will be restored.

5 20. The method of claim 19 wherein the coating process is performed after the impression process, and the sealing layer formed on the polymer composite layer fills the gaps of the polymer composite layer to prevent air permeation.

10 21. The method of claim 19 wherein the coating process is performed before the impression process, and the method further comprises a thermal process to soften the sealing layer after the impression process, so that the sealing layer can fill the gaps in the polymer composite layer to prevent air
15 permeation.

22. The method of claim 19 further comprising a second coating process to form a second sealing layer on the other side of the polymer composite layer.

20 23. The method of claim 19 wherein the polymer composite layer contains one or more layers each made by one of the following materials: acrylic resins, polyester, polyethylene (PE), polypropylene (PP), copolymer of PE and PP, ethylene-styrene copolymer (ES), cyclo olefin, polyethylene terephthalate
25 (PET), polyvinyl alcohol (PVA), ethylene-vinyl acetate (EVA), Surlyn™ (Dupont ionomer), polyethylene naphthalate (PEN), poly ether ether ketone (PEEK), polycarbonate (PC), polysulfone, polyimide (PI), polyacrylonitrile (PAN),
30 styrene acrylonitrile (SAN), polyurethane (PU), synthetic papers, glassine papers, polyolefin coated paper or paper-like materials.

24. The method of claim 19 wherein the sealing layer is made from fatty acids or their derivatives, starch, amyloid materials or their derivatives, lipids, oleaginous materials, wetting agents, or waxes.

25. The method of claim 24 wherein the waxes are natural waxes or synthetic waxes.

26. The method of claim 19 wherein the gaps are evenly distributed or distributed within selected areas of the polymer layer.

27. The method of claim 19 wherein the polymer composite layer or the sealing layer further comprises an oxygen scavenger for preventing oxygen from permeating through the composite film.

28. A method of manufacturing an air permeable packaging bag, the method comprising:
providing a polymer composite layer, the polymer composite layer comprising a plurality of gaps formed by using an impression process, the polymer composite layer comprising a first part and a second part;
folding the polymer composite layer to overlap the first part against the second part; and
performing a sealing process to seal the overlapping edges of the first part and second part so as to form an opening of the air permeable packaging bag.

29. The method of claim 28 wherein the sealing process is performed using a heat activating process, an ultrasonic pressing process, a zipper, a ziplock or an adhesive.

30. The method of claim 28 wherein the method of closing the opening
of the air permeable packaging bag uses a zipper, a ziplock,
a heat activating process, an ultrasonic pressing process, or
an adhesive.
31. A method of manufacturing an air permeable packaging bag, the
method comprising:
providing two polymer composite layers, at least one of the
two polymer composite layers comprising a plurality of
gaps formed by virtue of an impression process;
overlapping the two polymer composite layers; and
performing a sealing process to seal the overlapping edges
of the two polymer composite layers so as to form an opening
of the air permeable packaging bag.
32. The method of claim 31 wherein the surface of the polymer
composite layer further comprises a sealing layer.
33. The method of claim 31 wherein the sealing process is performed
using a heat activating process, an ultrasonic pressing
process, or an adhesive.
34. The method of claim 31 wherein the method of closing the opening
of the air permeable packaging bag uses a zipper, a ziplock,
a heat activating process, an ultrasonic pressing process,
or an adhesive.
35. An air permeable packaging bag comprising a folded polymer
layer, the folded polymer layer having a plurality of gaps
formed by virtue of an impression process and three overlapping
edges; wherein two of the three overlapping edges are sealed

so as to form an opening in the air permeable packaging bag.

36. The air permeable packaging bag of claim 35 further comprising a sealing layer formed on the surface of the polymer layer.

5

37. The method of claim 35 wherein the method of closing the opening of the air permeable packaging bag uses a zipper, a ziplock, a heat activating process, an ultrasonic pressing process or an adhesive.

10

38. An air permeable packaging bag comprising a first polymer layer and a second polymer layer laminated on the first polymer layer, at least one of the first and second layers comprising a plurality of gaps formed by virtue of an impression process, wherein three of the overlapping edges of the two polymer layers are sealed so as to form three sealed sides and an opening.

15

39. The air permeable packaging bag of claim 38 further comprising a sealing layer formed on the surface of the first and second polymer layers.

20

40. The method of claim 38 wherein the method of closing the opening of the air permeable packaging bag uses a zipper, a ziplock, a heat activating process, an ultrasonic pressing process or an adhesive.

25

41. A microwave tray for food cooking, comprising:
a tray having at least one space, and an open rim on the outer peripheral area of the tray; and
an air permeable composite film covering and sealing the tray,
the air permeable composite film comprising:

30

a polymer layer, the polymer layer being perforated by virtue of an impression process, thereby forming a plurality of gaps on the surface of the polymer layer; and a nonstick sealing layer covering and filling the gaps.


5

42. The microwave tray of claim 41 wherein the tray is made from the following materials: heat resistant polymeric materials, ceramics, glasses, wood, polyolefin coated paper or bamboo.

10 43. The microwave tray of claim 41 wherein the method of sealing the tray with the air permeable composite film includes using a rim secure socket, a ziplock, a heat sealing process, an ultrasonic pressing process, or an adhesive.

ABSTRACT OF THE INVENTION

A method for manufacturing a novel air permeable composite film is disclosed. The air permeable composite film has a polymer layer with a top face and a bottom face and a sealing layer covering the top face. The polymer layer is first perforated by virtue of an impression process to form a plurality of tiny gaps in it for air permeation. Then the sealing layer is coated on the top face of the polymer layer to fill the gaps. The differential pressure between the top face and bottom face of the polymer layer enlarges the gaps and makes the gaps become air permeable.






Fig. 2A




Fig. 2B




Fig. 2C




Fig. 3




Fig. 4




Fig. 5




Fig. 6

COMBINED DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

I believe I am the sole (if only one name appears below), or a joint (if more than one name appears), original and first inventor of the subject matter which is claimed and for which a patent is sought on the invention entitled:

“ Method for manufacturing an air permeable composite film ”

 + The specification for the above entitled invention is filed herewith.

 The specification for the above entitled invention was filed previously with application serial number: Filing Date:

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of the invention disclosed in this application in accordance with Title 37, Code of Federal Regulations, Section 1.56 (a). I further acknowledge the duty in any continuation-in-part application to disclose to the Patent and Trademark Office all information known to be material to the patentability of the invention disclosed in this application, as defined in 1.56, which became available to me between the filing date of the prior application and the filing date of this application.

PRIORITY CLAIM

 There is no claim of priority.

 + Claim of priority is based on the following:

POWER OF ATTORNEY

As a named inventor, I hereby appoint the following attorney to prosecute this application and to transact all related business in the Patent and Trademark Office:

Winston Hsu, Registration Number 41,526
3F, No.52, Lane 46, Min-Sheng Rd., YUNGHO City,
Taipei Hsien, Taiwan, R.O.C.
TEL: +886-2-2948-3200

DECLARATION

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment or both under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued hereon.

Date: 5/3/00 Irene Lin
Printed Name: Irene Lin
Post Office Address: 16F-1, No.93, Sec.2, Roosevelt Rd.,
and Residence: Taipei, Taiwan, R.O.C.
Citizen of: U.S.A.

Date: _____
Printed Name: _____
Post Office Address: _____
and Residence: _____
Citizen of: _____

Date: _____
Printed Name: _____
Post Office Address: _____
and Residence: _____
Citizen of: _____

Date: _____
Printed Name: _____
Post Office Address: _____
and Residence: _____
Citizen of: _____

Date: _____
Printed Name: _____
Post Office Address: _____
and Residence: _____
Citizen of: _____

001090704060400